



B-218-00/A1004

TECHNICAL DATA SHEET

Huntsman Solutions Bâtiments' **B218-00/A1004** is a two-component spray-applied rigid polyurethane foam system specially formulated for application like tanks and Pipes with high service temperature up to 121°C (250°F).

This product is manufactured with recycled plastic materials, rapidly renewable soy oils, and 4th generation blowing agent with zero ozone depleting potential and < 1 global warming potential. It uses zero ODS (Ozone Depletion Substance) blowing agents and meets all the requirements of the Montreal protocol to protect the ozone layer.

PHYSICAL PROPERTIES			
Density	2.4 – 2.6 lb/ft ³	38 – 42 kg/m ³	ASTM D 1622
Initial Thermal Resistance	R-7.27	1.28 RSI	ASTM C 518
Compressive Strength (10%)	33 psi	228 kPa	ASTM D 1621
Dimensional Stability (7 days) (% Volume change, sample without any substrate) @ -20°C @ 80°C @ 70°C, 100% H.R.		0.3 +0,1 -1,7	ASTM D 2126

LIQUID COMPONENT PROPERTIES*		
PROPERTY	A-PMDI ISOCYANATE	B218-00 RESIN
Color	Brown	Brown or Blue
Viscosity @ 25°C (77°F)	150 – 350 cps	450 – 550 cps
Specific Gravity	1.20 – 1.24	1.20 – 1.23
Shelf life of unopened drum properly stored*	12 months	6 months
Mixing Ratio (volume)	100	100
Storage Temperature	10 - 38°C (50 - 100°F)	15 - 25°C (59 - 77°F)

*See SDS for more information

RECOMMENDED PROCESSION PARAMETERS		
Mixing Ratio A/B (volume)	1/1	
Initial Primary Heaters Set Point	40 - 44°C	104 - 111°F
Initial Primary Hose Heat Set Point	40 - 44°C	104 - 111°F
Initial Processing Setpoint Pressure	5516 – 5860 kPa	800 – 850 psi
Minimal Recommend Processing Pressure	4482 kPa	650 psi
Ambient and Substrate Temperature	15 - 32°C	59 - 90°F
Maximum moisture content of substrate		19 %
Maximum thickness per pass	50 mm	2"
Maximum thickness of successive passes	100 mm	4"
Minimum cooling time period before applying over 100 mm (4') thick application		4 h

REACTIVITY PROFILE

Cream time	Gel time	Tack free time	End of rise
0 - 1 second	3 – 4 seconds	7 - 8 seconds	5 - 6 seconds

General Requirements: It is recommended that the foam be covered with an approved thermal barrier in accordance with the applicable building code when used in buildings and cover by a UV coating when used outside. This product should not be used when the continuous service temperature of the substrate is outside the range of -60°C to 121°C (-76°F to 250°F). Do not apply excessive thickness in one application it may cause spontaneous combustion of the foam hours after the application. Respect the recommended procedures.

Disclaimer: The information herein is to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, express or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent inferred. The exclusive remedy for all proven claims is replacement of our materials. All patent rights are reserved.

