



# HEATLOK HFO Pro

## TECHNICAL DATA SHEET

Heatlok® HFO Pro is a two component, HFO blown closed cell, spray applied, rigid polyurethane foam system covered by the scope of standard EN 14315-1. The product is used as a thermal insulation, air barrier and vapor barrier or retarder depending on the thickness applied. The product can be sprayed onto concrete, masonry, wood, metals, gypsum board and particle board.

For more information, look at the HBS Heatlok HFO PRO installation instructions.

### FOAM PROPERTIES

PHYSICAL PROPERTIES		
EN 1602	Apparent density	32 - 36 kg/m <sup>3</sup>
EN 12667	Thermal conductivity	20 ≤ d ≤ 200 mm    λ = 25 mW/m.K
EN 1609	Water permeability	W0,23
EN 12 086	Water vapour permeability	MU60
EN 1605	Deformation under specified compressive load and temperature conditions	DLT(1)5
EN 1604	Dimensional Stability (dimensional change)	DS(TH)3
EN 826	Compressive Strength	CS(10\Y)150
VOC	Release of dangerous substances	A+
EN ISO 4590	Closed cells content	CCC4

FIRE TEST RESULTS		
EN 13501-1+A1	Reaction to fire	Euroclass E

REACTIVITY PROFILE			
Cream Time	Gel Time	Tack Free Time	End of Rise
1 second	2 seconds	3 – 4 seconds	3 – 4 seconds

## CHEMICAL PROPERTIES

LIQUID COMPONENT PROPERTIES*		
PROPERTY	A-PMDI ISOCYANATE	HEATLOK HFO PRO RESIN
Color	Brown	Blue
Viscosity @ 25°C	ca. 200 mPas	ca. 350 mPas
Density @ 25°C	ca. 1.23 g/cm <sup>3</sup>	ca. 1.20 g/cm <sup>3</sup>
Specific Gravity	1.24 kg/dm <sup>3</sup>	1.17 - 1.21 kg/dm <sup>3</sup>
Shelf Life of unopened drum properly stored	12 months	6 months
Storage Temperature	15 - 30 °C	15 - 25 °C
Mixing Ratio (volume)	1:1	1:1
RECYCLED & RENEWABLE CONTENT		
Recyclable Content		12.5%
Renewable Content		1%

## PROCESSING CONDITIONS

RECOMMENDED PROCESSING CONDITIONS*	
Initial Primary Heater Setpoint Temperature	41 – 46 °C
Initial Hose Heat Setpoint Temperature	41 – 46 °C
Initial Processing Setpoint Pressure	85 - 95 bar
Substrate & Ambient Temperature (No humidity on the surface of the substrate)	> -5 °C
Moisture Content of timber substrate	≤ 19%
Moisture Content of Concrete	Concrete must be cured, dry and free of dust and form release agents.

\*Foam application temperatures and pressures can vary widely depending on temperature, humidity, elevation, substrate, equipment and other factors. While processing, the applicator must continuously observe the characteristics of the sprayed foam and adjust processing temperatures and pressures to maintain proper cell structure, adhesion, cohesion and general foam quality. It is the sole responsibility of the applicator to process and apply Heatlok HFO Pro within specification.

RECOMMENDED MAXIMUM PASS THICKNESSES	
Maximum Pass	50 mm

General Requirements: Equipment must be capable of delivering the proper ratio (1:1 by volume) of polymeric isocyanate (PMDI) and polyol blend at adequate temperatures and spray pressures. Substrate must be at least - 5 degrees, with best processing results when ambient humidity is below 80%. Substrate must also be free of moisture (dew or frost), grease, oil, solvents and other materials that would adversely affect adhesion of the polyurethane foam. Applicators should limit the application of this product to no more than a thickness of 50mm per pass (after expansion) to avoid fire hazards (including spontaneous combustion) resulting from excessive heat generation. If subsequent passes are needed, applicators should wait until the temperature of the foam surface has dropped below 38°C to allow any reaction heat to dissipate from the prior applications before attempting to re-apply the product.

## STORAGE AND USAGE

Heatlok HFO PRO component A should be stored between 15°C - 30°C and component B should be stored between 15°C - 25°C. Component A should be protected from freezing. The shelf life of component B is 6 months, component A is 12 months.

Do not store material on rigs other than what is required for the current application needs. Material left inside rigs can easily exceed this recommended temperature in the warmer months. The excessive heat will degrade the component B (resin) material and the blowing agent will gas out rendering the material useless.

If the material was transported in freezing conditions, store it in room temperature for a minimum of 24 hours to get proper material condition. Do not attempt to heat up drum during storage.

## HEALTH AND SAFETY

Every rig must have a first aid kit and must be equipped with an eye wash station. MSDS for the components are also mandatory wherever the HBS products are being stored or used.

Wearing the prescribed Personal Protective Equipment (PPE) is required when handling chemical components to prevent direct contact with the skin and the eyes. Please refer to the MSDS for the complete recommended handling procedures. Note: Different individuals will react differently to the same exposures, as some can be more sensitive than others.

HBS recommends that only trained applicators wearing the proper PPE and trained professionals wearing the proper PPE enter a 15-meter area surrounding the application of the spray foam during the 24 hours following that application. That 15-meter area needs to be ventilated at a 0.3 ACH (air change per hour) rate during the application and maintained for those initial 24 hours. Please refer to the table below for different re-occupancy time and their corresponding ACH conditions and restrain any person that is not wearing the proper PPE or is not trained by HBS from entering the 15 meters area in compliance with HBS re-occupancy conditions and recommendation. It is necessary to allow active ventilation of the site to ensure that emissions resulting from the applications are completely evacuated from the application zone.

## RE-ENTRY AND RE-OCCUPANCY PERIODS

Time based upon ventilation during and after spray application :24h at 40 ACH.

Number of air changes can be calculated using the following formula :

$$ACH = \frac{\text{Fan Power in l/s} * 3,6}{\text{Room Volume in m}^3}$$

If the number of ACH is not sufficient a bigger fan or multiple fans may be used

## PACKAGE

The components are supplied in barrels with capacity of 200 l.

Component A – 249 kg

Component B – 225 kg

## PRODUCT COMPLIANCE AND CERTIFICATIONS



**UKCA:**

This product is fully compliant with British Standards.



**Kiwa:**

a trustworthy certification body.