



# MAXGUARD® P-855

## TECHNICAL DATA SHEET

**Maxguard® P-855** is a two component, spray applied, 100% solid polyurethane elastomeric membrane system. Maxguard P-855 has good chemical resistance, excellent toughness and abrasion resistance. However, this elastomer is not stable under the effect of UV light. A color stabilizing additive is available upon request. Various colorants are available for the end users to blend with the B-side (polyol component).

Common Uses: Agriculture and aquatic pond liner (alligator ponds), faux rock coating, foam blocks & encapsulation.

PHYSICAL PROPERTIES			
Tensile Strength	2300 – 2900 psi	15.9 – 20.0 Mpa	ASTM D 412 C
Elongation	60 – 80%		ASTM D 412 C
Shore D Hardness	55 – 65		ASTM D 2240
Tear Resistance	350 – 400 pli		ASTM D 4060

LIQUID COMPONENT PROPERTIES*		
PROPERTY	A-109	MAXGUARD P-855 B
Color	Yellow	Transparent pale yellow, can be colored
Viscosity @ 77°F (25°C)	400 – 500 cps	200 – 500 cps
Specific Gravity @ 77°F (25°C)	1.13 – 1.17	1.05 – 1.15
Shelf Life of unopened drum properly stored	6 months	6 months
Storage Temperature	59 – 86°F (15 – 30°C)	59 – 86°F (15 – 30°C)
Mixing Ratio (volume)	1:1	1:1

\*See SDS for more information.

REACTIVITY PROFILE	
Gel Time @ 77°F (25°C)	
3 – 5 seconds	

RECOMMENDED PROCESSING CONDITIONS*		
Initial Primary Heater Setpoint Temperature	140°F	60°C
Initial Hose Heat Setpoint Temperature	140°F	60°C
Initial Processing Setpoint Pressure	1800 – 2500 psi	12411 – 17237 kPa
Substrate & Ambient Temperature	> 41°F	> 5°C

\*It is the sole responsibility of the applicator to process and apply Maxguard P-855 within specification.

**General Requirements:** Equipment must be capable of delivering the proper ratio (1:1 by volume) of isocyanate and resin at adequate temperatures and spray pressures. Substrate must be at least 5°F above dew point, with a maximum relative humidity of 80%. Substrate must also be free of moisture (dew or frost), grease, oil, solvents and other materials that would adversely affect adhesion of the product. This product must not be used when the continuous service temperature of the substrate or product is below -10°F (-23°C) or above 140°F (60°C).

**Disclaimer:** The information herein is to assist customers in determining whether our products are suitable for their applications. We request that customers inspect and test our products before use and satisfy themselves as to contents and suitability. Nothing herein shall constitute a warranty, expressed or implied, including any warranty of merchantability or fitness, nor is protection from any law or patent inferred. All patent rights are reserved. The product is combustible and must be protected in accordance with applicable codes. Protect from direct flame and spark contact, around hot work for example. The exclusive remedy for all proven claims is replacement of our materials.