

# ICC-ES Evaluation Report

**ESR-5499**

Issued May 2024


This report also contains:

**- FBC Supplement**

Subject to renewal May 2025

ICC-ES Evaluation Reports are not to be construed as representing aesthetics or any other attributes not specifically addressed, nor are they to be construed as an endorsement of the subject of the report or a recommendation for its use. There is no warranty by ICC Evaluation Service, LLC, express or implied, as to any finding or other matter in this report, or as to any product covered by the report.

Copyright © 2024 ICC Evaluation Service, LLC. All rights reserved.

<p><b>DIVISION: 07 00 00 — THERMAL AND MOISTURE PROTECTION</b></p> <p><b>Section: 07 21 00 — Thermal Insulation</b></p>	<p><b>REPORT HOLDER:</b></p> <p><b>HUNTSMAN BUILDING SOLUTIONS</b></p>	<p><b>EVALUATION SUBJECT:</b></p> <p><b>ICYNENE OC NO-MIX SPRAY FOAM INSULATION</b></p>	
---	--	---	---

## 1.0 EVALUATION SCOPE

### 1.1 Compliance with the following codes:

- 2021, 2018, 2015, 2012 and 2009 [International Building Code® \(IBC\)](#)
- 2021, 2018, 2015, 2012 and 2009 [International Residential Code® \(IRC\)](#)
- 2021, 2018, 2015, 2012 and 2009 [International Energy Conservation Code® \(IECC\)](#)
- 2013 *Abu Dhabi International Building Code (ADIBC)*<sup>†</sup>

<sup>†</sup>The ADIBC is based on the 2009 IBC. 2009 IBC code sections referenced in this report are the same sections in the ADIBC.

- Other Codes (see Section 8.0)

### Properties evaluated:

- Surface-burning characteristics
- Physical properties
- Thermal resistance (*R*-values)
- Air permeability
- Attic and crawl space installation
- Fire-resistance-rated construction

### 1.2 Evaluation to the following green standard:

- 2008 [ICC 700 National Green Building Standard™](#) (ICC 700-2008)

### Attribute verified:

- See Section 2.0

## 2.0 USES

Icynene OC No-Mix spray foam insulation is used as a nonstructural thermal insulating material in buildings of Type V construction under the IBC and dwellings under the IRC. The insulation is for use in wall cavities, floor assemblies or ceiling assemblies and in attic and crawl space applications as described in Section 4.4. Icynene OC No-Mix spray foam insulation may be used as an air-impermeable insulation. Icynene OC No-Mix may also be used in fire-resistance-rated wall assemblies when constructed in accordance with Section 4.5 of this report.

The attributes of the insulation have been verified as conforming to the provisions of ICC 700-2008 Section 703.2.1.1.1(c) as an air impermeable insulation. Note that decisions on compliance for those areas rest with the user of this report. The user is advised of the project-specific provisions that may be contingent upon meeting specific conditions, and the verification of those conditions is outside the scope of this report. These codes or standards often provide supplemental information as guidance.

## 3.0 DESCRIPTION

### 3.1 Foam-LOK FL500:

Icynene OC No-Mix spray foam insulation is a low-density, cellular polyurethane foam plastic that is installed as a nonstructural component of floor/ceiling and wall assemblies. The material is a two-component, open-cell, one-to-one-by-volume spray foam with a nominal density of 0.5 pcf. The polyurethane foam is produced in the field by combining an isocyanate "A" component and a polymeric resin "B" component. The components have a shelf life of six months when stored in factory-sealed containers at temperatures between 50°F and 80°F (10°C and 27°C). The insulation liquid components are supplied in nominally 55-gallon drums.

### 3.2 Surface-burning Characteristics:

The insulation at a maximum thickness of 5.6 inches (142 mm) and a nominal density of 0.5 pcf, has a flame-spread index of 25 or less and smoke-developed index of 450 or less when tested in accordance with ASTM E84.

### 3.3 Thermal Resistance (R-values):

The insulation has thermal resistance (*R*-values), at a mean temperature of 75°F (24°C), as shown in [Table 1](#).

### 3.4 Air Permeability:

Icynene OC No-Mix spray foam insulation at a minimum thickness of 4<sup>1</sup>/<sub>2</sub> inches (114 mm) is considered air-impermeable in accordance with 2021, 2018, 2015 and 2012 IRC Section R806.5 [2009 IRC Section R806.4], based on testing in accordance with ASTM E283.

### 3.5 DC 315 Coating:

DC 315 Coating, manufactured by International Fireproof Technology, Inc./ Paint to Protect Inc. ([ESR-3702](#)), is a water-based intumescent coating supplied in 5-gallon (19 L) pails and 55-gallon (208 L) drums and has a shelf life of twenty four months when stored in a factory-sealed container at temperatures between 50°F and 80°F (10°C and 27°C).

## 4.0 INSTALLATION

### 4.1 General:

Icynene OC No-Mix spray foam insulation must be installed in accordance with the manufacturer's published installation instructions, the applicable code and this report. A copy of the manufacturer's published installation instructions must be available at all times on the jobsite during installation.

### 4.2 Application:

The insulation is spray-applied on the jobsite using a volumetric positive displacement pump as identified in the Huntsman Building Solutions LLC's application instructions. The Icynene OC No-Mix resin "B" component must be stored at temperatures between 50°F (10°C) and 80°F (27°C). The insulation is used in areas where the maximum ambient temperature is equal to or less than 180°F (82°C). The foam plastic must not be used in electrical outlet or junction boxes or in contact with water. The foam plastic must not be sprayed onto a substrate that is wet, or covered with frost or ice, loose scales, rust, oil, or grease. The insulation must be protected from the weather during and after application. The Icynene OC No-Mix insulation may be spray-applied in one pass up to the maximum thicknesses specified in Section 4.3.

### 4.3 Thermal Barrier:

**4.3.1 Application with a Prescriptive Thermal Barrier:** The Icynene OC No-Mix spray foam insulation must be separated from the interior of the building by an approved thermal barrier of 1/2-inch-thick (12.7 mm) gypsum wallboard or an equivalent 15-minute thermal barrier complying with, and installed in accordance with, IBC Section 2603.4 or IRC Section R316.4, as applicable. Thicknesses of up to 12 inches (305 mm) for ceiling cavities and 12 inches (305 mm) for wall cavities are recognized based on room corner fire testing in accordance with NFPA 286, when the insulation is covered with minimum 1/2-inch-thick (12.7 mm) gypsum wallboard or an equivalent 15-minute thermal barrier complying with, and installed in accordance with, the applicable code.

**4.3.2 Application without a Prescriptive Thermal Barrier:** The prescriptive 15-minute thermal barrier may be omitted when installation is in accordance with this section. The insulation and DC 315 Coating, described in Section 3.5 and recognized in [ESR-3702](#), may be spray-applied to the interior facing of walls, the underside

of roof sheathing, and in crawl spaces, and may be left exposed as an interior finish without the prescribed 15-minute thermal barrier. The thickness of the foam applied to the underside of roof sheathing must not exceed 11<sup>1</sup>/<sub>4</sub> inches (286 mm). The thickness of the foam applied to vertical wall surfaces must not exceed 5<sup>1</sup>/<sub>4</sub> inches (133 mm). The foam plastic must be covered on all exposed surfaces with the DC 315 Coating at a minimum wet film thickness of 20-mil (0.51 mm) [dry film thickness of 13 mils (0.33 mm) or 1 gallon (3.8 L) per 80 square feet (7.4 m<sup>2</sup>)]. The DC 315 Coating must be applied over the Icynene OC No-Mix insulation in accordance with the coating manufacturer's instructions, [ESR-3702](#) and this report. Surfaces to be coated must be dry, clean, and free of dirt, loose debris and any other substances that could interfere with adhesion of the coating.

#### 4.4 Use in Attics and Crawl Spaces:

**4.4.1 Application with a Prescriptive Ignition Barrier:** When the spray-applied insulation is installed within attics and crawl spaces, where entry is made only to service utilities, an ignition barrier must be installed in accordance with IBC Section 2603.4.1.6 or IRC Sections R316.5.3 and R316.5.4, as applicable. The ignition barrier must be consistent with the requirements for the type of construction required by the applicable code and must be installed in a manner so that the foam plastic insulation is not exposed.

**4.4.2 Application without a Prescriptive Ignition Barrier:** Icynene OC No-Mix spray-applied polyurethane foam insulation may be installed in attics and crawl spaces as described in Sections 4.4.2 and 4.4.3 without the ignition barriers described in IBC Section 2603.4.1.6 and IRC Sections R316.5.3 and R316.5.4, subject to the following conditions:

- a. Entry to the attic or crawl space is only to service utilities, and no storage is permitted.
- b. There are no interconnected attic or crawl space areas.
- c. Air in the attic or crawl space is not circulated to other parts of the building.
- d. Attic ventilation is provided when required by 2021 and 2018 IBC Section 1202.2 [2015, 2012 and 2009 IBC Section 1203.2] or IRC Section R806, as applicable, except when air-impermeable insulation is permitted in unvented attics in accordance with 2021 and 2018 IBC Section 1202.3 [2015 IBC Section 1203.3] or 2021, 2018, 2015 and 2012 IBC Section R806.5 [2009 IRC Section R806.4], as applicable. Under-floor (crawl space) ventilation is provided when required by 2021 and 2018 IBC Section 1202.4 [2015, 2012 and 2009 IBC Section 1203.3] or IRC Section R408.1, as applicable.
- e. Combustion air is provided in accordance with IMC (*International Mechanical Code*) Section 701.
- f. If hot work is to be performed, all necessary procedures, precautions and limitations must be observed in accordance with OSHA 1926 Subpart J Standard 1926.352 requirements for hot work (welding / cutting) performed in the vicinity of combustible materials.
- g. An installation certificate with the following information must be posted at each entrance:
  - Product name and installation thickness.
  - Manufacturer name, address and contact information.
  - Installation contractor name, address and contact information.
  - Attestation that the product(s) have been installed in accordance with the manufacturer's installation instructions and the requirements of the evaluation report.
  - A notice that the certificate is not to be removed or altered.
  - A list of limitations for the space including the following:
    - o Entry to the space is only to service utilities, and no storage is permitted.
    - o FIRE SAFETY WARNING: If hot work is to be performed, all necessary procedures, precautions and limitations must be observed in accordance with OSHA 1926 Subpart J Standard 1926.352 requirements for hot work (welding / cutting) performed in the vicinity of combustible materials.

In attics, the insulation may be spray-applied to the underside of roof sheathing or roof rafters, and/or to vertical surfaces; and in crawl spaces, the insulation may be spray-applied to the underside of floors and/or vertical surfaces. The thickness of the foam plastic, applied to the underside of the top of the space, must not exceed 11<sup>1</sup>/<sub>2</sub> inches (292 mm). The thickness of the foam plastic applied to vertical surfaces must not exceed 5<sup>1</sup>/<sub>2</sub> inches (140 mm). The foam plastic must be covered on all exposed surfaces with the DC 315 coating, described in Section 3.5, at a minimum wet film thickness of 4 mils (0.10 mm) (dry film thickness of 3 mils (0.08 mm) or 1 gallon (3.8 L) per 400 square feet (37.1 m<sup>2</sup>)). The DC 315 coating must be applied over the Icynene OC No-Mix insulation in accordance with the coating manufacturer's instructions and this report. Surfaces to be coated must be dry, clean, and free of dirt, loose debris and any other substances that could interfere with adhesion of the coating. The coating must be applied when ambient and substrate temperatures

are a minimum of 50°F time. The assembly described in this section may be installed in unvented attics in accordance with 2021 and 2018 IBC Section 1202.3 [2015 IBC Section 1203.3] or 2021, 2018, 2015 and 2012 IRC Section R806.5 [2009 IRC Section R806.4], as applicable, when the foam plastic is applied to a minimum depth of 4<sup>1</sup>/<sub>2</sub> inches (114 mm).

**4.4.3 Use on Attic Floors:** Icynene OC No-Mix spray-applied polyurethane foam insulation may be installed at a maximum thickness of 5<sup>1</sup>/<sub>2</sub> inches (140 mm) between the joists in an attic floor. The insulation must be covered with DC 315 coating applied as described in Section 4.4.2. The insulation must be separated from the interior of the building by an approved thermal barrier.

#### **4.5 One-hour Fire-resistance-rated Exterior Wall Assemblies (Non-load-bearing):**

Icynene OC No-Mix insulation may be used as a component of one-hour fire-resistance-rated, non-load-bearing wall assemblies as described in Section 4.5.1 or 4.5.2.

##### **4.5.1 One-hour Wood-framed Wall Assembly:**

**4.5.1.1 Interior and Exterior Face:** One layer of <sup>5</sup>/<sub>8</sub>-inch-thick (15.9 mm), Type X gypsum board, complying with ASTM C36 or ASTM C1396, installed with the long edge parallel to the studs on both sides of nominal 2-inch by 6-inch wood, No. 2 Grade, Southern Yellow Pine, studs spaced 16 inches (406 mm) on center. The gypsum board is secured with 1<sup>1</sup>/<sub>4</sub>-inch-long (32 mm) Type W drywall screws spaced 8 inches (203 mm) on center along the perimeter and in the field. Gypsum board joints must be taped, and joints and fastener heads treated with joint compound to Level 2 finish in accordance with ASTM C840 or GA-216.

**4.5.1.2 Stud Cavity:** Nominally 5<sup>1</sup>/<sub>2</sub>-inch-thick Icynene OC No-Mix foam insulation is spray-applied in all stud cavities.

##### **4.5.2 One-hour Steel-framed Wall Assembly:**

**4.5.2.1 Interior and Exterior Face:** Two layers of <sup>5</sup>/<sub>8</sub>-inch-thick (15.9 mm), Type X gypsum board, complying with ASTM C36 or ASTM C1396, is installed on both sides of 3<sup>5</sup>/<sub>8</sub>-inch-deep (92 mm), No. 20 gage, galvanized steel studs spaced 24 inches (610 mm) on center. The base layer of the gypsum board is installed with the long edge parallel to the studs and secured with No. 6 by 1<sup>1</sup>/<sub>4</sub>-inch-long (32 mm), self-drilling drywall screws 8 inches (203 mm) on center along the perimeter and 12 inches (305 mm) on center in the field of the wallboard. The face layer of the wallboard is secured with No. 6 by 1<sup>7</sup>/<sub>8</sub>-inch-long (48 mm), self-drilling drywall screws 8 inches (203 mm) on center along the perimeter and in the field of the wallboard. The joints must be staggered from the base layer the face layer and from interior to exterior face of the assembly. Gypsum board joints must be taped, and joints and fastener heads treated with joint compound to Level 2 finish in accordance with ASTM C840 or GA-216.

**4.5.3 Stud Cavity:** Nominally 3<sup>5</sup>/<sub>8</sub>-inch-thick Icynene OC No-Mix foam insulation is spray-applied in all stud cavities.

## **5.0 CONDITIONS OF USE:**

The Icynene OC No-Mix spray foam insulation described in this report complies with, or is a suitable alternative to what is specified in, those codes listed in Section 1.0 of this report, subject to the following conditions:

- 5.1** This evaluation report and the manufacturer's published installation instructions, when required by the code official, must be submitted at the time of permit application.
- 5.2** The Icynene OC No-Mix spray foam insulation must be installed in accordance with the manufacturer's published installation instructions, this evaluation report and the applicable code. If there are conflicts between this report and the manufacturers' published installation instructions, this report governs.
- 5.3** The insulation must be separated from the interior of the building by an approved 15-minute thermal barrier, except when installation is as described in Section 4.3.2 or 4.4.2.
- 5.4** The insulation must not exceed the nominal density and thicknesses noted in Sections 3.2, 4.3, 4.4, and 4.5.
- 5.5** The insulation must be protected from the weather during and after application.
- 5.6** The insulation must be applied by contractors certified by Huntsman Building Solutions, LLC.
- 5.7** Use of the insulation in areas where the probability of termite infestation is "very heavy" must be in accordance with IRC Section R318.4 or 2021, 2018, 2015 and 2009 IBC Section 2603.8 [2012 IBC Section 2603.9], as applicable.
- 5.8** The insulation has been evaluated only for use in Type V construction under the IBC and in dwellings under the IRC.
- 5.9** Jobsite certification and labeling of the insulation must comply with 2021, 2018 or 2015 IRC Sections N1101.10.1 and N1101.10.1.1 [2012 IRC Sections N1101.12.1 and N1101.12.1.1 or 2009 IRC Sections

N1101.4 and N1101.4.1] and 2021, 2018, 2015 and 2012 IECC Sections C303.1.1, C303.1.1.1, R303.1.1 and R303.1.1.1 [2009 IECC Sections 303.1.1 and 303.1.1.1.], as applicable.

- 5.10** When installed in accordance with Section 4.4.2 of this report, the associated installation certificate(s) containing the required information referenced in Section 4.4.2 must be installed at each entrance to the crawlspace or attic, as applicable. The certificate(s) must be red in color and constructed of durable materials, such as metal, plastic, or laminated paper.
- 5.11** When used in unvented attics in accordance with Section 4.4.2 of this report, installation with a vapor diffusion port in accordance with 2021 IBC Section 1202.3, Item 5.2 or 2021 and 2018 IRC Section R806.5, Item 5.2 is outside the scope of this report.
- 5.12** A vapor retarder must be installed as required by the applicable code.
- 5.13** The components of the insulation are produced in Houston, Texas, under a quality control program with inspections by ICC-ES.

## 6.0 EVIDENCE SUBMITTED

- 6.1** Data in accordance with the [ICC-ES Acceptance Criteria for Spray-applied Foam Plastic Insulation \(AC377\)](#), dated June 2023, including tests in accordance with Appendix X of AC377.
- 6.2** Reports of air leakage tests in accordance with ASTM E283.
- 6.3** Reports of room corner fire testing in accordance with NFPA 286.
- 6.4** Reports of testing in accordance with ASTM E970.
- 6.5** Reports of testing in accordance with ASTM E119.

## 7.0 IDENTIFICATION

- 7.1** Components for Icynene OC No-Mix spray foam insulation are identified with the manufacturer's name (Huntsman Building Solutions), address and telephone number; the product name (Icynene OC No-Mix); mixing instructions; the density; the flame-spread and smoke-development indices; the shelf life and production date or the expiration date; and the evaluation report number ([ESR-5499](#)).

International Fireproof Technology, Inc. / Paint to Protect Inc., DC 315 coating is labeled with the manufacturer's name and address; the product name; the date of manufacture, the shelf life or expiration date; the manufacturer's instructions for application, and evaluation report number ([ESR-3702](#)).

- 7.2** The report holder's contact information is the following:

**HUNTSMAN BUILDING SOLUTIONS**  
**3315 EAST DIVISION STREET**  
**ARLINGTON, TEXAS 76011**  
**(817) 640-4900**  
[www.huntsmanbuildingsolutions.com](http://www.huntsmanbuildingsolutions.com)

## 8.0 OTHER CODES

In addition to the codes referenced in Section 1.0, the products described in this report were evaluated for compliance with the requirements of the following codes:

- 2006 *International Building Code*® (2006 IBC)
- 2006 *International Residential Code*® (2006 IRC)
- 2006 *International Energy Conservation Code*® (2006 IECC)

The products comply with the above-mentioned codes as described in Sections 2.0 through 7.0 of this report, with the revisions noted below:

- **Application with a Prescriptive Thermal Barrier:** See Section 4.3.1, except the approved thermal barrier must be installed in accordance with Section R314.4 of the 2006 IRC.
- **Application with a Prescriptive Ignition Barrier:** See Section 4.4.1 except attics must be vented in accordance with Section 1203.2 of the 2006 IBC, and crawl space ventilation must be in accordance with Section 1203.3 of the 2006 IBC or 2006 IRC Section R408, as applicable. Additionally, an ignition barrier must be installed in accordance with Sections R314.5.3 or R314.5.4 of the 2006 IRC, as applicable.
- **Application without a Prescriptive Ignition Barrier:** See Section 4.4.2, except attics must be vented in accordance with Section 1203.2 of the 2006 IBC, and crawl space ventilation must be in accordance with

Section 1203.3 of the 2006 IBC or 2006 IRC Section R408, as applicable. Combustion air is provided in accordance with Sections 701 and 703 of the 2006 IECC.

- **Protection against Termites:** See Section 5.7, except use of the insulation in areas where the probability of termite infestation is “very heavy”, must be in accordance with Section R320.5 of the 2006 IRC.
- **Jobsite Certification and Labeling:** See Section 5.9, except jobsite certification and labeling must comply with Sections 102.1.1 and 102.1.11, as applicable, of the 2006 IECC.

**TABLE 1—THERMAL RESISTANCE (R-VALUES)**

THICKNESS (inches)	R-VALUE (°F.ft <sup>2</sup> .h/Btu)
1	3.8
2	7.6
3	11.3
3.5	13.2
4	15.0
5	18
6	21.8
7	25.5
8	29
9	32.8
10	36.4
11	40
12	43.7

For **SI**: 1 inch = 25.4 mm; 1°F.ft<sup>2</sup>.h/Btu = 0.176 110°K.m<sup>2</sup>/W.  
<sup>1</sup>R-values are calculated based on tested K-values at 1- and 4-inch thicknesses.

**DIVISION: 07 00 00—THERMAL AND MOISTURE PROTECTION**  
**Section: 07 21 00—Thermal Insulation**

**REPORT HOLDER:**

**HUNTSMAN BUILDING SOLUTIONS**

**EVALUATION SUBJECT:**

**ICYNENE OC NO-MIX SPRAY FOAM INSULATION**

**1.0 REPORT PURPOSE AND SCOPE**

**Purpose:**

The purpose of this evaluation report supplement is to indicate that Icynene OC No-Mix spray foam insulation, described in ICC-ES evaluation report ESR-5499, has also been evaluated for compliance with the codes noted below.

**Applicable code editions:**

- 2020 *Florida Building Code—Building*
- 2020 *Florida Building Code—Residential*

**2.0 CONCLUSIONS**

The Icynene OC No-Mix spray foam insulation, described in Sections 2.0 through 7.0 of the evaluation report ESR-5499, complies with the *Florida Building Code—Building* and the *Florida Building Code—Residential*, provided the design and installation are in accordance with the 2018 *International Building Code*® provisions noted in the evaluation report under the following condition:

Installation must meet the requirements of Sections 1403.8 and 2603.8 of the *Florida Building Code – Building* and Sections R318.7 and R318.8 of the *Florida Building Code – Residential*, as applicable.

Use of the Icynene OC No-Mix spray foam insulation for compliance with the High-Velocity Hurricane Zone provisions of the *Florida Building Code—Building* and the *Florida Building Code—Residential* has not been evaluated, and is outside the scope of this evaluation report.

For products falling under Florida Rule 61G20-3, verification that the report holder’s quality assurance program is audited by a quality assurance entity approved by the Florida Building Commission for the type of inspections being conducted is the responsibility of an approved validation entity (or the code official when the report holder does not possess an approval by the Commission).

This supplement expires concurrently with the evaluation report, issued May 2024.